

Nickel Bath NORMA

Nickel Bath NORMA is a sturdy electrolyte which is operated in most cases without additives, which is mainly used for plating of intermediate nickel layers in the field of electrical and electronic application. Its deposits are very ductile and extremely active which is especially important for subsequent electroplating. On blank surfaces Nickel Bath NORMA produces light and relatively uniform nickel coatings.

The information in this data sheet is based on laboratory as well as practical experience. Figures quoted for operating limits and replenishment quantities are for guidance. Actual values necessary will depend on the components being plated (material and geometry), their application and plating plant conditions.

Important:

Please read this instruction carefully prior to the use of the process and carefully follow all the parameters that have a direct influence on the operation. We reserve the right to make technical changes. In the interest of safety, please pay attention to the hazard warnings on the labels of the containers. The minimum shelf life of the products is included on the labels and is also available in the appropriate Quality Assurance (QA03).

The current IMDS number of the layer deposited from the process is available on the internet at www.schloetter.com/downloads.

For the storage of chemical products the TRGS 510 must be followed.

If the additives used in this process contain a SVHC-substance, then this will be specified in the corresponding Material Safety Data Sheet, section 15.

