

Degreaser

SLOTOCLEAN AK 10

The Degreaser SLOTOCLEAN AK 10 is a highly effective immersion degreaser, even at relatively low operating temperatures. It is mainly intended for the removal of oil, grease or drawing compounds from steel. Copper and its alloys can also be cleaned. However, it should be noted, that brass may slightly tarnish during prolonged treatment.

The Degreaser SLOTOCLEAN AK 10 is designed so that already at 40 - 50 °C heavy dirt can be removed.

The good conductivity of Degreaser SLOTOCLEAN AK 10 allows also anodic degreasing of steel and non-ferrous metals.

The Degreaser SLOTOCLEAN AK 10 is suitable for both rack- and barrel applications.

Degreaser SLOTOCLEAN AK 10 is operated with two components, Degreaser Salt SLOTOCLEAN AK 11 and a degreaser additive/cleaning enhancer according to the assigned task. Our Summary Degreaser Additives (BATH 02300-E) informs you about the different possible combinations.

The information in this data sheet is based on laboratory as well as practical experience. Figures quoted for operating limits and replenishment quantities are for guidance. Actual values necessary will depend on the components being plated (material and geometry), their application and plating plant conditions.

Important:

Please read this instruction carefully prior to the use of the process and carefully follow all the parameters that have a direct influence on the operation. We reserve the right to make technical changes. In the interest of safety, please pay attention to the hazard warnings on the labels of the containers. The minimum shelf life of the products is included on the labels and is also available in the appropriate Quality Assurance (QA03).

The current IMDS number of the layer deposited from the process is available on the internet at www.schloetter.com/downloads.

For the storage of chemical products the TRGS 510 must be followed.

If the additives used in this process contain a SVHC-substance, then this will be specified in the corresponding Material Safety Data Sheet, section 15.

