

Application of Corrector SOB

The Corrector SOB is used in static rinses to correct brownish or yellowish surface discolouration of silver plated parts, caused by prolonged transport or dwell times in static rinses of automatic plating plants.

Rinse water with Corrector SOB content may furthermore be used for replenishment of the electrolyte.

The information in this data sheet is based on laboratory as well as practical experience. Figures quoted for operating limits and replenishment quantities are for guidance. Actual values necessary will depend on the components being plated (material and geometry), their application and plating plant conditions.

Important:

Please read these instructions carefully and follow recommendations given. We reserve the right to make technical changes as necessary. In the interests of safety, please pay attention to the R- and S- phrases on the labels of the containers. The minimum shelf life of the additives is printed on the label of the container. The current IMDS number of the layer deposited from the process can be found on the internet at www.schloetter.com/downloads.

For the storage of chemical products only the TRGS 514 and TRGS 515 regulations must be followed. The Hazardous Goods Regulation (ADR/GGVS) is only valid **for transportation** and must not be applied to storage.

